



# P317

## Chopped Strands for BMC

### PRODUCT DESCRIPTION

P317 Chopped Strands are made from E-glass continuous filaments treated with a polyester-compatible sizing.



### PRODUCT REFERENCE

Example : EC 17 6 mm P317  
E : glass type  
C : continuous process  
17 : nominal length of chop (mm)  
P317 : OCV™ Reinforcements code for sizing system

### PRODUCT APPLICATION

P317 are particularly suitable for producing compounds intended for either compression or injection molding in the production of thermoset composites.

### FEATURES AND PRODUCT BENEFITS

- Easy mixing into the resin
- Because of their whiteness P317 BMC Chopped Strands do not color the compound
- No pollution, e.g. colored particles
- Regular mechanical properties in both compression-molded and injection-molded parts

### TECHNICAL CHARACTERISTICS (NOMINAL VALUES)

LINEAR WEIGHT (TEX)	MOISTURE (%)
ISO 1887	ISO 3344
0.75	< 0.1

# P317

## Chopped Strands for BMC

### PACKAGING

Examples of collective packaging:

PRODUCT		NET WEIGHT OF BAGS (KG)	NUMBER OF BAGS PER PALLET	PALLET DIMENSION LXWXH (CM)	NET WEIGHT OF PALLET*
P317	6 mm	20	33	120 x 90 x 115	660
	12 mm	15	33		495

\* Add 35 to 45 kg to obtain gross weight.

### STORAGE

The Chopped Strands should be stored in its original packaging in a dry and cool place. Best conditions are at temperature from 10 to 35°C and humidity between 35 and 85 %. If you store the product at lower temperatures, please move the soon to be processed pallets to the production area 24 hours ahead of time. You can stock pallets one on one with a plywood plank in between the two.

#### Contact

BMCChoppedStrands.ocvamericas@owenscorning.com    BMCChoppedStrands.ocvemea@owenscorning.com    BMCChoppedStrands.ocvap@owenscorning.com



## OCV™ Reinforcements

**OWENS CORNING  
COMPOSITE MATERIALS, LLC**  
ONE OWENS CORNING PARKWAY  
TOLEDO, OHIO 43659  
1.800.GET.PINK™  
www.owenscorning.com  
www.ocvreinforcements.com

**EUROPEAN OWENS CORNING  
FIBERGLAS, SPRL.**  
166, CHAUSSÉE DE LA HULPE  
B-1170 BRUSSELS  
BELGIUM  
+32.2.674.82.11

**OWENS CORNING - OCV ASIA PACIFIC  
SHANGHAI REGIONAL HEADQUARTERS**  
2F OLIVE LVO. MANSION  
620 HUA SHAN ROAD  
SHANGHAI 200040  
CHINA  
+86.21.62489922

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.