



Cem-FIL® 60/3

AR Chopped Strands for Premix GRC


PRODUCT DESCRIPTION

Cem-FIL® 60/3 is a high integrity AR glass fibre chopped strand designed for premixing with other materials and the resulting mix is formed by vibration casting or other processes into moulded GRC components.

PRODUCT APPLICATION

The high integrity of the product makes it suitable for use in a variety of production processes including vibration-casting, pumping, spraying, or dry-blending with other materials.

Cem-FIL® 60/3 chopped strands are designed for ease of incorporation even at high dosage and remain integral during mixing. It is used in the manufacture of standard GRC components such as drainage channels or meter boxes, or in architectural applications such as decorative screen walling and ornate mouldings. **Cem-FIL® 60/3's** hydrophobic behaviour makes the mix more fluid and that ensures better compaction and easier release of trapped air.



FEATURES AND PRODUCT BENEFITS

- Alkali resistant glass*
- High integrity
- High level of workability
- Reduced water demand / greater strength
- Easy incorporation
- Abrasion resistant strand
- Improves mechanical performance of GRC elements
- Safe and easy to handle

* Our fibres are manufactured with high Zirconia content in compliance with ASTM C1666/C 1666/M-07 and EN 15422 and under the recommendations of PCI and GRCA

TECHNICAL CHARACTERISTICS (nominal values)

Fibre Length	Fibre Diameter	Tex	Size Content (%)	Moisture (%)
			ISO 1887 : 1980	ISO 3344 : 1977
6 - 12 - 18 (mm)	14 (µm)	82	0.8	0.3 max
¼" - ½" - ¾" (in)	0.000546 (in)			

Cem-FIL® 60/3

AR Chopped Strands for Premix GRC

Cem-FIL® 60/3 chopped strands are packed in individual plastic bags. The plastic bags are packed on a timber pallet with a cardboard outer container for protection. The completed pallets are wrapped in polyethylene and identified with two labels.

STORAGE

Cem-FIL® 60/3 chopped strands should be stored away from heat and moisture, and in their original packaging. The best conditions are:

- Temperature: 15 °C – 35 °C.
- Humidity: 35 % – 65 %.


If the product is stored at lower temperatures it is advisable to condition it in the workshop for at least 24 hours before use, to prevent condensation.

OCV™ Reinforcements recommends using the material according to FIFO (first in, first out) method.

QUALITY

Cem-FIL® 60/3 chopped strands are manufactured under a quality Management System approved to ISO 9001. Additionally the actual performance of Cem-FIL® 60/3 is subject to independent assessment and approval in Germany (Zulassung n° Z-3.72.1731).

PALLET CHARACTERISTICS



NORTH AMERICA

James PATTERSON
TEL: +1 623.566.0260
FAX: +1 208.730.4581
Cem-fil@owenscorning.com

EUROPE

Holger ZORN
TEL: +32.2.674.8318
FAX: +32.2.662.0815
Cem-fil@owenscorning.com

ASIA PACIFIC

Peter RIDD
TEL: +44 1275.390.968
FAX: +44 117.370.1075
Cem-fil@owenscorning.com

MIDDLE EAST AND AFRICA

Brian MARTEN
FAX: +44 (0) 870.1123811
Cem-fil@owenscorning.com



OCV™ Reinforcements

OWENS CORNING

COMPOSITE MATERIALS, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK™
www.owenscorning.com
www.ocvreinforcements.com

EUROPEAN OWENS CORNING

FIBERGLAS, SPRL.
166, CHAUSSÉE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32.2.674.82.11

OWENS CORNING – OCV ASIA PACIFIC

SHANGHAI REGIONAL HEADQUARTERS.
2F OLIVE LVO. MANSION
620 HUA SHAN ROAD
SHANGHAI 200040
CHINA
86.21.62489922

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.

Pub. No. 10010689. Owens Corning reserves the right to modify this document without prior notice. ©2009 Owens Corning