



P215

Multi-End Roving for SMC

PRODUCT DESCRIPTION

P215 is a multi-end roving, manufactured from a collection of continuous glass strands which are gathered, without mechanical twist, into a single bundle. The roving is then wound and shipped as a tubeless package ready for use at customer operations. P215 roving is manufactured with state-of-the-art equipment, innovative chemistry and with a major commitment to statistical process control. OCV Reinforcements uses a Quality Management System certified to meet ISO 9002 standards.



PRODUCT APPLICATION

P215 is a multi-end E-glass roving with low sub-tex, designed for the manufacture of Sheet Molding Compound (SMC). P215 sizing is of medium solubility (60%) and contains a Silane coupling agent. Due to its outstanding characteristics, P215 roving is particularly recommended for application where very good surface aspect is requested.



FEATURES AND PRODUCT BENEFITS

- | | |
|---|---|
| <ul style="list-style-type: none"> • Excellent processability | <ul style="list-style-type: none"> • Easy unwinding and chopping • Good strand distribution • No fuzz • No static electricity |
| <ul style="list-style-type: none"> • Easy wet-out and impregnation | |
| <ul style="list-style-type: none"> • Very good properties of moulded parts | <ul style="list-style-type: none"> • Good surface aspect • No coloration • Highly pigmentable • Good mechanical properties |

TECHNICAL CHARACTERISTICS (nominal values)

Linear weight of roving (TEX) (g/km)	Loss on Ignition (%)	Moisture (%)
ISO 1889	ISO 1887	ISO 3344
2400	1.25	< 0.15

P215

Multi-End Roving for SMC

PRODUCT AVAILABILITY (standard reference)

Identification Number	Bare glass linear density (tex)	Approx. pkg weight (kg)	Available Package
EC 2400 P215	2400	19.0	Bulk Pack, Creel-Pak

Note: E : Type of glass
C : Type of process, continuous
P215 : OCV Reinforcements code for sizing system

PACKAGING AND PALLETIZATION (standard reference)

Pallet Dimensions

Pallet Height, cm (in)	95 (37)
Pallet Length, cm (in)	114 (45)
Pallet Width, cm (in)	114 (45)
Pallet Weight, net, kg (lb)	912 (2011)
Number of layers	3
Package per pallet	48

Package Dimensions

Package Height, cm (in)	26.5(10)
Package Diameter, cm (in)	28(11)
Package Weight, kg (lb)	19 (42)

STORAGE

Unless otherwise specified, it is recommended to store glass fibre products in original packaging in a cool dry area. The best conditions are at temperature between 15°C and 35°C and at a relative humidity between 35% and 85%. If these conditions are respected, glass fibre products should not undergo significant changes when stored for extended periods of time. If storage temperature is less than 15°C it is recommended that rovings be transferred to the workshop at least 24 hours before intended processing, in order to prevent condensation. The packaging system is designed to allow stacking of two pallets. When stacking two high, care should be taken to correctly and smoothly place the top pallet. It is recommended to use plywood plate between the two pallets in order not to damage the lower pallet.



OCV™ Reinforcements

**OWENS CORNING
COMPOSITE MATERIALS, LLC**
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK™
www.owenscorning.com
www.ocvreinforcements.com

Contact:
MultiEndRovings.ocvamericas@owenscorning.com

**EUROPEAN OWENS CORNING
FIBERGLAS, SPRL.**
166, CHAUSSÉE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32.2.674.82.11

Contact:
MultiEndRovings.ocvemea@owenscorning.com

**OWENS CORNING - OCV ASIA PACIFIC
SHANGHAI REGIONAL HEADQUARTERS**
2F OLIVE LVO. MANSION
620 HUA SHAN ROAD
SHANGHAI 200040
CHINA
+86.21.62489922

Contact:
MultiEndRovings.ocvap@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.

Pub. No. 10010186-A. Owens Corning reserves the right to modify this document without prior notice. © 2009 Owens Corning.

MultiEndRov_P215_ap_08-2008_Rev1