



PZ

Multi-End Roving for Spray-Up

PRODUCT DESCRIPTION

PZ is a multi-end roving produced using Advantex® glass fiber. Advantex® glass fiber combines the electrical and mechanical properties of traditional E-glass with the acid corrosion resistance of E-CR glass.

This E-glass roving has a sizing system with a silane coupling agent. It has been designed to provide overall performance for spray-up applications.



FEATURES AND PRODUCT BENEFITS

- Easy rolling and de-airing

TECHNICAL CHARACTERISTICS (NOMINAL VALUES)

LINEAR WEIGHT (TEX)	LOSS ON IGNITION (%)	MOISTURE (%)
ISO 1889 : 1997	ISO 1887 : 1995	ISO 3344 : 1997
2400	1% +/- 0.15	≤ 0.15

PZ

Multi-End Roving for Spray-Up

PACKAGING

Product	Pallet Dimensions L X W (cm)	Levels Per Pallet	Cheeses Per Level	Total Number of Cheeses	PALLETS	
					Approx. Height (cm)	Net Weight* (kg)
PZ	114 x 114	4	16	64	119	1300

* Add 35 to 45 kg to obtain gross weight

STORAGE

PZ roving should be stored dry and in its original packaging. The best conditions are temperature between 10 and 35°C and at a relative humidity between 35 and 85%.

If the product is stored at low temperature (below 15°C) it is necessary to put the pallets to be processed for at least 24 hours prior their use into processing area and remove a part of protective cover of the pallet to prevent condensation of humidity. Static stacking of the pallets is possible one plus one (1/1), but it is recommended to use a plywood plate between the two pallets in order not to damage the lower pallet.

Contact

MultiEndRovings.ocvamericas@owenscorning.com

MultiEndRovings.ocvemea@owenscorning.com

MultiEndRovings.ocvap@owenscorning.com



OCV™ Reinforcements

**OWENS CORNING
COMPOSITE MATERIALS, LLC**
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK™
www.owenscorning.com
www.ocvreinforcements.com

**EUROPEAN OWENS CORNING
FIBERGLAS, SPRL.**
166, CHAUSSÉE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32.2.674.82.11

**OWENS CORNING - OCV ASIA PACIFIC
SHANGHAI REGIONAL HEADQUARTERS**
2F OLIVE LVO. MANSION
620 HUA SHAN ROAD
SHANGHAI 200040
CHINA
+86.21.62489922

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.