




366

Single-End Roving for Pultrusion and Filament Winding Processes

PRODUCT DESCRIPTION

Single-End Rovings are produced by pulling individual fibers directly from the bushing and winding them onto a roving package ready for shipment. The uniform distribution of a proprietary sizing system ensures an excellent resin-to-glass binding through uniform distribution of the binding agent. This results in maximum strand integrity.

Single-End Rovings are manufactured using the T30® Roving state-of-the-art technology of Owens Corning, in conjunction with statistical process control in manufacturing facilities certified to ISO 9001.



© J.L. Sponga

PRODUCT APPLICATION

366 Roving is specifically designed for use in pultrusion and filament winding applications in polyester, vinylester and epoxy resin systems. 366 has also been successfully used in acrylic resin and polyurethane resin systems.

366 can be used in a variety of processes to manufacture pipes, tanks, ladder rails, pultruded structural shapes and grating systems.



FEATURES AND PRODUCT BENEFITS

- Excellent processing
 - 366 has no catenary, which means it will run out smoothly throughout the package under a variety of conditions and speeds.
 - 366 has low fuzz properties that will result in smoother parts, less cleanup and improved machine efficiencies.
 - The Tack-Pak® packaging allows virtually 100 percent transfer efficiency.
- Multi-resin compatible
 - The silane-based sizing of 366 is designed for excellent adhesion with polyester, vinyl ester and epoxy resin systems. Multi-compatibility allows a change in resin systems without the need for the time consuming effort of changing glass in the creel. In addition, 366 has had great success in acrylic and polyurethane resin systems.
- Excellent strand opening and spreading
 - 366 allows fast, uniform wet out of the strand in all resin systems. Fast wet out should allow for optimized part fabrication time, increased productivity and improved competitive position in the market.
- Available globally
 - 366 product line is available globally in a wide variety of yields and TEX. Global availability allows for one product qualification rather than designing or modifying product or processes by region. Global availability results in lower design and qualification costs.

366

Single-End Roving for Pultrusion and Filament Winding processes

PRODUCT AVAILABILITY

Yield	Tex
675, 450, 330, 250, 207, 113	2200, 2400, 4400, 8000, 9600

MECHANICAL PROPERTIES

The following data was generated using production material 366 – 113 Yield (4400 tex)

Strand Tensiles : ASTM D 2343	Strength (MPa)	Strength (Ksi)
DER 331 Epoxy resin	2360	340
Polyester F701 Resin	2300	335

Interlaminar Shear Strength NOL ring : ASTM D 2344	Dry shear strength (MPa)	Dry shear strength (psi)	shear strength Retention 72 hr boil (%)
DER 331 Epoxy resin	61.6	8940	98%
Polyester F701 Resin	72.5	10520	86%

PACKAGING

Rovings are available in a single-end internal-pull package. Each pallet weighed about 1 ton. Pallets are stretch wrapped for load stability. All doffs are wrapped with Tack-Pak® or shrinkable film for protection during transport. Full doffs are available in weights between 20 kg (45 lb.) and 40 kg (88 lb.) and they can be packaged in bulk or Creel-Pak® format. More information is available in the Customer Acceptance Standards

STORAGE

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. The glass fiber products must remain in their original packaging material until the point of usage. If these conditions are maintained, the glass fiber product should not undergo significant changes when stored for one year. Beyond one year after delivery, the product might evolve, specifically if stored outside the recommended conditions.

The best storage conditions are: temperatures between 22°C and 23°C and humidity between 60% and 65%.

The product should be stored in the workshop, within its original packaging, 48 hours prior to its utilization.



**OWENS CORNING
COMPOSITE MATERIALS, LLC**
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK™

www.owenscorning.com
www.ocvreinforcements.com

Contact:
SingleEndRovings.ocvamericas@owenscorning.com

**OWENS CORNING
FIBERGLAS, SPRL.**
166, CHAUSSÉE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32 267 48211

Contact:
SingleEndRovings.ocvmea@owenscorning.com

**OWENS CORNING
OCV ASIA PACIFIC**
SHANGHAI REGIONAL HEADQUARTERS
2F OLIVE LVO MANSION 620 HUA SHAN ROAD
SHANGHAI 200040
CHINA

+86 262 489 922
Contact:
SingleEndRovings.ocvap@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.