



Single-End Rovings (Type 30®)

OCV™ Reinforcements is the pioneer in both Multi and Single-End roving and has been making glass for more than 50 years. OCV™ Reinforcements developed the Single-End Roving process and trademarked Type 30® over 30 years ago. OCV™ Reinforcements manufactures Single-End Rovings globally with advanced equipment, innovative surface chemistry and a commitment to process control.

The result is a ready supply of products to meet the most exciting performance and cost requirements. Ongoing development work continues to refine the performance of single-End Rovings with one customer benefit in mind, increased productivity.

PRODUCT DESCRIPTION

Single-End Rovings are reinforcement products for filament winding, long-fiber thermoplastics, pultrusion, knitting and weaving applications with polyester (UP), vinylester (VE), epoxy (EP), phenolic (PN), polypropylene (PP), polyamide (PA) resin systems. Single-End Rovings are produced by pulling individual fibers directly from the bushing and winding them onto a roving package ready for shipment. The uniform distribution of a proprietary sizing system ensures an excellent resin-to-glass binding through uniform distribution of the binding agent.

GLOBAL QUALITY

OCV™ Reinforcements continues to meet ongoing customer demands for higher productivity, higher value products and excellent support. Single-End Rovings are produced with a global process, which ensures high quality and consistency in all regions of the world while meeting performance and cost requirements.



Our worldwide technical and marketing network provides our customers with products and services that continue to meet evolving needs.

ADVANTEX® AND SINGLE-END ROVINGS

In recent years, OCV™ Reinforcements began making Single-End Rovings with the company's Advantex® glass fiber reinforcements. Advantex® glass fiber reinforcements combine the electrical and mechanical properties of traditional E-glass with the acid corrosion resistance of E-CR glass. Advantex® glass fiber reinforcements are compatible with all of the most widely used resin systems. Processability and production characteristics of Advantex® glass fiber reinforcements are comparable to traditional E-glass and E-CR glass formulations.

FEATURES AND PRODUCT BENEFITS

- | | |
|--|---|
| • Superior processing | • Optimized to maximize equipment uptime |
| • Fast wet-out | • Increased productivity |
| • Optimum package and pallet weight | • Better productivity, less storage space, fewer pallet changes |
| • Excellent laminate mechanical properties | • Meets or exceeds physical properties requirements for a broad range of applications |
| • Excellent packaging run out and transfer | • More complete glass utilization and reduced labor cost |

Single-End Rovings (Type 30®)

GLOBAL RANGE FOR THERMOSET RESINS

PRODUCT	REGION				RESIN COMPATIBILITY				PROCESS			
	NA	LA	EMEA	AP	UP	VE	EP	PN	Fil. Winding	Pultrusion	Weaving	Muffler Filling
111A		•	•	•	•	•	•			•	•	
SE1200	•	•	•	•	•	•	•	•	•	•	•	
SE1500	•	•	•	•			•		•	•	•	
366	•			•	•	•	•		•	•		
399	•		•	•	•	•	•			•		
699		•		•				•		•		
SEB400LS	•		•		•	•	•			•		
R25H		•	•	•	•	•	•		•	•		
158B	•	•		•			•	•	•			
SE2348	•			•			•		•			
SE2350	•			•			•		•			
FW300				•	•				•			
FW35				•					•			
117A			•						•		•	
202			•						•			
ST2070			•	•								•
ST1048			•	•								•
ST2000	•											•

PACKAGING

Rovings are available in a single-end internal-pull package. Each pallet weighed about 1 ton. Pallets are stretch wrapped for load stability. All doffs are wrapped with Tack-Pak® transport. Full doffs are available in weights of 20 kg (45 lb.) and 40 kg (88 lb.) regionally and they can be packaged in bulk or Creel-Pak® format.

STORAGE

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. The packaging is

not waterproof. Be sure to protect the product from the weather and other sources of water. The glass fiber products must remain in their original packaging material until the point of usage. If these conditions are maintained, the glass fiber product should not undergo significant changes when stored for one year. Beyond one year after delivery, the product might evolve, specifically if stored outside the recommended conditions.

The best storage conditions are :

- Temperatures between 22°C and 23°C
- Humidity between 60% and 65%.

The product should be stored in the workshop, within its original packaging, 48 hours prior to its utilization.

Contact

SingleEndRovings.ocvamericas@owenscorning.com

SingleEndRovings.ocvemea@owenscorning.com

SingleEndRovings.ocvap@owenscorning.com



OCV™ Reinforcements

**OWENS CORNING
COMPOSITE MATERIALS, LLC**
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK™
www.owenscorning.com
www.ocvreinforcements.com

**EUROPEAN OWENS CORNING
FIBERGLAS, SPRL.**
166, CHAUSSÉE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32.2.674.82.11

**OWENS CORNING - OCV ASIA PACIFIC
SHANGHAI REGIONAL HEADQUARTERS**
2F OLIVE LVO. MANSION
620 HUA SHAN ROAD
SHANGHAI 200040
CHINA
+86.21.62489922

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.