

## CEM-FIL® 61

### GRC PREMIX AND SPRAY ROVING



#### DESCRIPTION

- **Cem-FIL® 61** is an Alkali Resistant glass fiber assembled roving designed for use in the manufacture of glass fiber reinforced concrete (GRC) composites by both premix and simultaneous spray methods.

#### BENEFITS

- Alkali resistant glass\*
- Good unwinding
- Easy chopping
- High split efficiency
- Safe and easy to handle
- Very easy incorporation into the matrix
- Great for use with complicated profiles
- Excellent reproduction of detail
- Excellent mechanical performance
- Makes highly durable GRC elements
- Suitable for both premix and spray

#### APPLICATIONS

- In the premix process, Cem-FIL® 61 is chopped into small strands with high abrasion resistance
- The fiber remains integral and this provides easy incorporation into the matrices and efficient workability
- Cem-FIL® 61's new sizing technology reduces the water absorption of the fiber strand, allowing a reduction in the water content of the matrix, or an increase in the fiber content
- In the spray process, Cem-FIL® 61 has good split efficiency and easy chopping with low fuzz generation.
- Cem-FIL® 61's hydrophobic behaviour makes the mix fluid and that ensures good compaction and easy release of trapped air

\* Our fibers are manufactured with high Zirconia content in compliance with ASTM C1666/C 1666/M-07 and EN 15422 and under the recommendations of PCI and GRCA



# CEM-FIL® 61

GRC PREMIX AND SPRAY ROVING

## TECHNICAL CHARACTERISTICS

Linear density of Roving (Tex) (ISO 1889 : 2009)	Linear density of Strand (Tex) (ISO 1889 : 2009)	Loss on Ignition (%) (ISO 1887 : 1995)	Moisture (%) (ISO 3344 : 1997)
2500	82	1.75	0.50 max.

- Assembled Roving
- Electrical Conductivity: Very low
- Specific Gravity: 2.68 g/cm<sup>3</sup>
- Material: Alkali Resistant Glass\*
- Softening point: 860°C – 1580°F
- Chemical Resistance: Very high
- Modulus of elasticity: 72 GPa – 10 x 10<sup>6</sup> psi
- Tensile Strength: 1000–1700 MPa – 145–250 x 10<sup>3</sup> psi

\* Our fibers are manufactured with high Zirconia content in compliance with ASTM C1666/C 1666/M-07 and EN 15422 and under the recommendations of PCI and GRCA

## DOSAGE

Cem-FIL® 61 rovings are used in GRC manufacturing processes with purpose-made GRC equipment. The recommended dosage in sprayed GRC is 5% by weight. The recommended dosage in premix GRC is 3% by weight.

## PACKAGING AND STORAGE

Cem-FIL® 61 rovings are protected by a shrink-wrap polythene film, open at the top which should not be removed when the product is in use. Rovings are packed on pallets either with or without carton boxes. Cem-FIL® 61 rovings should be stored away from heat and moisture, and in their original packaging. Optimum conditions are temperature between 15°C and 35°C and humidity between 35% and 65%. If the product is stored at lower temperatures it is advisable to condition it in the workshop for at least 24 hours before use, to prevent condensation.

## QUALITY STANDARDS – CERTIFICATION

Cem-FIL® 61 fibers are manufactured under a quality Management System approved to ISO 9001.

Cem-FIL® fibers are not classified as dangerous by the Regulation 1272/2008/EC. For more information, please refer to our Safe Use Instructions Sheet.

For further info please send a email to: [cem-fil@owenscorning.com](mailto:cem-fil@owenscorning.com) / [www.cem-fil.com](http://www.cem-fil.com)

### Americas

Owens Corning  
Composite Materials, LLC.  
One Owens Corning Parkway  
Toledo  
Ohio 43659  
1.800.get.pink™  
+1-623-566-0206

### Europe

European Owens Corning  
Fiberglas Sprl.  
166 Chaussée de la Hulpe  
B-1170 Brussels  
Belgium  
+33.479.75.5300

### Asia Pacific

Owens Corning - OC Asia Pacific  
Shanghai Regional Headquarters  
Unit 01, 02,05, 39/F,  
Pudong Kerry Parkside,  
1155 Fang Dian Road, Pudong, Shanghai,  
201204, China  
+86-21-6101 9666

This information and data contained herein is offered solely as a guide in the selection of reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.

Owens Corning reserves the right to modify this document without prior notice. © 2014 Owens Corning. All Rights Reserved.  
Pub number: 10010685. CemFIL 61\_product sheet\_ww\_10-2014\_Rev8\_EN. October 2014

[Cem-fil@owenscorning.com](mailto:cem-fil@owenscorning.com)  
[www.cem-fil.com](http://www.cem-fil.com)